

Test Report

Report No.: DGF250911039HE01

Page 1 of 8

Applicant : Xi'an Yingdeen Handicraft Co., Ltd.
Address : Rm1-1502, Chuangxin Business apartment, No.69, Jinye Rd, Gaoxin zone, Xi'an, Shaanxi, China

The following sample(s) was/were submitted and identified on behalf of the client as:

Product Name : Glass canister with wooden lids
Model : 21989
Material : High borosilicate glass, wooden lids, silicone sealing ring

Date of Sample Received : Sept. 11, 2025
Test period : Sept. 11, 2025 - Oct. 29, 2025

Test requested:

For material which contact with foodstuff, selected tests were performed for compliant with the following regulations:

- Regulation 1935/2004/EC on materials and articles intended to come into contact with food;
- Council Directive 84/500/EEC relating to ceramic articles intended to come into contact with foodstuffs and amendment regulation 2005/31/EC.
- Resolution AP(2004)2 On cork stoppers and other cork materials and articles intended to come into contact with foodstuffs.
- Resolution AP(2004)5 on silicones used for food contact applications.
- Regulation (EU) 2024/3190 On the use of bisphenol A (BPA) and other bisphenols and bisphenol derivatives with harmonised classification for specific hazardous properties in certain materials and articles intended to come into contact with food.

Test method: : Please refer to next page.

Test result : Please refer to next page.

**Approved by:**

Handwritten signature of Richard Ke in black ink.

Richard Ke
(Signed for and on behalf)

Date:

Oct. 29, 2025



Test Report

Report No.: DGF250911039HE01

Page 2 of 8

Test Results:

1. Method: With reference to BS EN 1388-2:1996, determined by ICP-MS.

Test Items	Test Conditions	Unit	MDL	Limit	Results	Conclusion
					No.1	
Migration of Lead (Pb)	4% acetic acid, 22°C, 24h	mg/L	0.01	4.0	N.D.	Pass
Migration of Cadmium (Cd)		mg/L	0.001	0.3	N.D.	Pass

2 Pentachlorophenol content test

Method: With reference to in-house method# and measured by LC-MS/MS.

Test Items	Unit	Limit	MDL	Result	Conclusion
				No.2	
Pentachlorophenol (PCP)	mg/kg	0.15	0.05	N.D.	Pass

Test Report

Report No.: DGF250911039HE01

Page 3 of 8

3.

Sensorial Examination Odour and Taste Test:

It is examined to what extent food simulant, which comes into contact with the product, undergoes detectable changes in taste and smell. For this purpose the product is immersed in the water under conditions stated bellow. After this time the food simulant is examined by 5 tasters with regard to any divergence in smell and taste. Another test sample, which is used as a reference, is treated the same way except that it has no contact with the product to be tested.

Method: With reference to DIN 10955:2024#.

Test Items	Simulation solvents and test conditions	Limit	Result	Conclusion
Odour	DI water, 40°C, 10d	2.5	0	Pass
Taste		2.5	0	Pass

Evaluation scheme for the transfer of taste and smell:

0=no discernible deviation

1=barely discernible deviation

2=weak deviation

3=clear deviation

4=strong deviation

Test Report

Report No.: DGF250911039HE01

Page 4 of 8

3.2 Overall Migration test

Method: With reference to

BS EN 1186-1:2002 for selection of conditions and test methods;

EN 1186-3:2022 Test methods for overall migration into aqueous food simulants by total immersion;

Test condition	Unit	Limit	Results	Conclusion
			No.3	
Overall migration in 10% ethanol, 40°C, 10d	mg/dm ²	10	<3.0	Pass

3.3 BPA content test:

Method: With reference to in-house method#, determined by LC-MS/MS;

Test item	Unit	Limit	MDL	Results	Conclusion
				No.3	
BPA	µg/kg	Absent	1	N.D.	Pass

Test Report

Report No.: DGF250911039HE01

Page 5 of 8

Test Part Description:

Group No.	Picture No.	Test Part Name
No.1	1	Transparent glass
No.2	2	Yellow wood
No.3	3	Semi-transparent silicone rubber

Note:

- (1) mg/kg=ppm=0.0001%; mg/dm² = milligram per square decimeter;
- (2) mg/L = milligram per litre; µg/kg=Microgram kilogram;
- (3) < = less than; ≤ = less than or equal to;
- (4) N.D. = Not Detected (<MDL);
- (5) MDL= Method Detection Limit;
- (6) Unless otherwise specified, refer to ILAC-G8:09/2019 and use the binary decision rule of simple acceptance (W=0) for conformity assessment.
- (7) “#” CNAS accredited project does not include this method.

Test Report

Report No.: DGF250911039HE01

Page 6 of 8

Photograph of Sample:




1

Test Report

Report No.: DGF250911039HE01

Page 7 of 8



Test Report

Report No.: DGF250911039HE01

Page 8 of 8

声明: Statement:

- 1.检测报告无批准人签字、“检测专用章”或“报告章”无效;
1.This report is considered invalid without approved signature, Detection special seal or Report seal;
- 2.样品及样品信息由申请者提供, 申请者应对其真实性负责, NTEK 未核实其真实性;
2. The sample(s) and sample information was/were provided by the client who should be responsible for the authenticity which NTEK hasn't verified;
3. 本报告检测结果仅对受测样品负责;
3. The result(s) shown in this report refer(s) only to the sample(s) tested;
4. 未经 NTEK 书面同意, 不得部分复制本报告;
4. Without written approval of NTEK, this report can't be reproduced except in full;
5. 如检测报告中的英文内容与中文内容有差异, 以中文为准。
5. In case of any discrepancy between the English version and Chinese version of the testing reports(if generated), the Chinese version shall prevail.

备注:报告未加盖 CMA 资质章时, 本报告中的数据结果仅供科研、教学、企业内部质量控制、企业产品研发等目的用。

Remark: When the report without CMA qualification seal, the testing data and result(s) in this report is(are) just for scientific research, education, internal quality control and product development etc.

End of Report

Dongguan NTEK Testing Technology Co., Ltd.

Address: Building 3, Meisaidaxin Park, Keji 8th Road, Songshan Lake High-Tech Industrial Development Zone,
Dongguan, Guangdong, China

Tel: (+86-769) 23301666

Fax: (+86-769) 23301600

Email: service@gdntek.cn

<http://www.dgntek.org.cn>